

**European Technical Approval****ETA 11/0427****Trade Name**

1. 3M™ High Intensity Prismatic Reflective Sheeting Series 3930 printed with 3M™ process colour series 4700
2. 3M™ High Intensity Prismatic Reflective Sheeting Series 3930 + 3M™ Piezo Inkjet Ink Series 8800UV + 3M™ Electrocut Film 1170
3. 3M™ High Intensity Prismatic Reflective Sheeting Series 3930 + 3M™ Piezo Inkjet Ink Series 8800UV + 3M™ Dew Resistant Overlay Film 1180
4. 3M™ High Intensity Prismatic Reflective Sheeting Series 3930 + 3M™ Premium Protective Overlay Film 1160
5. 3M™ High Intensity Prismatic Reflective Sheeting Series 3930 + 3M™ Electrocut Film Series 1170 + 3M™ Premium Protective Overlay Film 1160
6. 3M™ High Intensity Prismatic Reflective Sheeting 3930 + 3M™ Electrocut Film 1176 with or without 3M™ Protective Overlay Film

**Holder of the approval**

3M Deutschland GmbH  
Carl-Schurz-Str. 1  
D- 41453 Neuss, Germany

**Website**

[www.3m.com](http://www.3m.com)

**Generic type and use of construction product**

Micro-prismatic retro-reflective sheeting for traffic signs

**Validity from:**

2013-06-27

**to**

2018-06-26

**Manufacturing plant(s):**

3M Deutschland GmbH Plant Hilden, Düsseldorferstr. 121-125, D-40705 Hilden, Germany  
3M Brownwood, Texas 76801 - US

**This European Technical Approval replaces:**

ETA 11/0427, valid from 13/12/2011 until 12 /12/2016

**This European Technical Approval contains:**

23 pages including 1 annex which form an integral part of the document



European Organisation for Technical Approvals  
Organisation Européenne pour l'Agrément Technique  
Europäische Organisation für Technische Zulassungen

## I. LEGAL BASES AND GENERAL CONDITIONS

1. This European Technical Approval is issued by UBAtc in accordance with:
  - Council Directive 89/106/EEC of 21 December 1988 on the approximation of laws, regulations and administrative provisions of Member States relating to construction products<sup>1</sup>, modified by Council Directive 93/68/EEC<sup>2</sup> and Regulation (EC) N° 1882/2003 of the European Parliament and of the Council<sup>3</sup>,
  - Belgian law of 25 March 1996 concerning the adaptation of legislative and administrative provisions of Member States to the Construction Products Directive (89/106/EEC) for construction products<sup>4</sup> and Belgian Royal Decree of 18 August 1998 concerning construction products<sup>5</sup>
  - Common Procedural Rules for Requesting, Preparing and the Granting of European Technical Approvals set out in the Annex to Commission Decision 94/23/EC<sup>6</sup>
2. The UBAtc is authorized to check whether the provisions of this European Technical Approval are met. Checking may take place in the manufacturing plant(s). Nevertheless, the responsibility for the conformity of the products to the European Technical Approval and for their fitness for the intended use remains with the holder of the European Technical Approval.
3. This European Technical Approval is not to be transferred to manufacturers or agents of manufacturers other than those indicated on page 1, or manufacturing plants other than those laid down in the context of this European Technical Approval.
4. This European Technical Approval may be withdrawn by UBAtc, in particular pursuant to information by the Commission according to Article 5(1) of Council Directive 89/106/EEC.
5. Reproduction of this European Technical Approval including transmission by electronic means shall be in full. However, partial reproduction can be made with the written consent of UBAtc. In this case partial reproduction has to be designated as such. Texts and drawings of advertising brochures shall not contradict or misuse the European Technical Approval.
6. Subject to the ETA application introduced, this European Technical Approval is issued by the approval body in its official languages. These versions correspond fully to the version circulated in EOTA. Translations into other languages have to be designated as such.
7. The ETA holder confirms to guarantee that the product(-s) to which this approval relates, is/are produced and marketed in accordance with and comply with all applicable legal and regulatory provisions, including, without limitation, national and European legislation on the safety of products and services. The ETA-holder shall notify the UBAtc immediately in writing of any circumstance affecting the aforementioned guarantee. This approval is issued under the condition that the aforementioned guarantee by the ETA holder is continuously observed.

---

<sup>1</sup> Official Journal of the European Communities N° L 40, 11.2.1989, p. 12

<sup>2</sup> Official Journal of the European Communities N° L 220, 30.8.1993, p. 1

<sup>3</sup> Official Journal of the European Union N° L 284, 31.10.2003, p. 1

<sup>4</sup> Belgian Law Gazette, 21.05.1996

<sup>5</sup> Belgian Law Gazette, 11.09.1998

<sup>6</sup> Official Journal of the European Communities N° L 17, 20.1.1994, p. 34

## II. SPECIFIC CONDITIONS OF THE EUROPEAN TECHNICAL APPROVAL

### 1 Definition of product and intended use

#### 1.1 General

The product consists of a micro-prismatic retro-reflective sheeting made of optical prismatic lenses elements formed in a transparent synthetic resin, sealed and backed with a pressure sensitive adhesive to form a durable bond to the sign substrates. The sheeting has a smooth surface with a distinctive interlocking seal pattern and may or may not have orientation marks, visible from the face.

The product is supplied as a single coloured sheet whose trade name is "3M™ High Intensity Prismatic Reflective Sheeting series 3930", or as a single coloured sheet with a coloured overlay film whose trade name is "3M High Intensity Prismatic Reflective Sheeting series 3930 + 3M™ Electrocut Film series 1170" or as a single coloured sheet printed with process colour whose trade name is "3M™ High Intensity Prismatic Reflective Sheeting series 3930" printed with "3M™ Process Colour Series 880, 4700 or Piezo

Inkjet Ink Series 8800 UV", possibly with an additional protection by 3M™ Dew Resistant Overlay Film 1180 or 3M™ Premium Protective Overlay Film 1160 or 3M™ Protective Overlay Film 1150.

3M™ Process Colour Series 880 I and 880 N are variations of the same basic ink formulations. Both ink series use identical pigments. The difference between 880I and 880N is the solvent package, providing different drying characteristics. 3M sells and markets both ink series as equal alternatives with the same durability and warranty provisions.

In case of digital printing, Process Colour Series 8800 UV are generally protected by a colourless overlay film, e.g. Electrocut Film 1170, Overlay Film 1160 or Overlay Film 1180.

#### 1.2 Components

An overview of the complete set of components of "3M™ High Intensity Prismatic Reflective Sheeting series 3930", and combinations with or without "3M™ Electrocut Film series 1170" or "Process Colour Series 880 I & N, Series 4700 or Piezo Inkjet Ink Series 8800 UV", and with or without 3M™ Dew Resistant Overlay Film 1180 or 3M™ Premium Protective Overlay Film 1160 or 3M™ Protective Overlay Film 1150 is presented in Table 1.

ETA 11/0426 contains	<ol style="list-style-type: none"> <li>3M™ High Intensity Prismatic Reflective Sheeting Series 3930</li> <li>3M™ High Intensity Prismatic Reflective Sheeting Series 3930 + 3M™ Electrocut Film Series 1070</li> <li>3M™ High Intensity Prismatic Reflective Sheeting Series 3930 printed with 3M™ Process Colour series 880 I or N</li> </ol>
This ETA contains ; Initial performance and performance after accelerated artificial weathering Use option 1, see Annex 1	<ol style="list-style-type: none"> <li>3M™ High Intensity Prismatic Reflective Sheeting Series 3930 printed with 3M™ Process Colour series 4700</li> <li>3M™ High Intensity Prismatic Reflective Sheeting Series 3930 + 3M™ Piezo Inkjet Ink Series 8800UV + 3M™ Electrocut Film 1170</li> <li>3M™ High Intensity Prismatic Reflective Sheeting Series 3930 + 3M™ Piezo Inkjet Ink Series 8800UV + 3M™ Dew Resistant Overlay Film 1180</li> <li>3M™ High Intensity Prismatic Reflective Sheeting Series 3930 + 3M™ Premium Protective Overlay Film 1160</li> <li>3M™ High Intensity Prismatic Reflective Sheeting Series 3930 + 3M™ Electrocut Film Series 1070 + 3M™ Premium Protective Overlay Film 1160</li> <li>3M™ High Intensity Prismatic Reflective Sheeting 3930 + 3M™ Electrocut Film 1176 with or without 3M™ Protective Overlay Film</li> </ol>

**Table 1 - Components of the product**

Components	Trade name	Colours/code	Characteristics	
Micro-prismatic retro-reflective sheeting	3M™ High Intensity Prismatic Reflective Sheeting Series 3930	White Red Yellow Green Blue	3930* 3932* 3931* 3937* 3935*	Thickness: 0,32 - 0,49 mm Rolls in various lengths and widths
Overlay film	3M™ ELECTROCUT FILM series 1170	Yellow Red Blue Green Brown Dark Green (Green 2) Colourless	1171* 1172* 1175* 1177* 1179* 1176 1170	Combined Thickness: 0,549 mm Rolls in various length and widths
Process colour	3M™ Process Colour Series 880 I or N	Yellow Blue Green French Red	884I or N* 883I or N* 888I or N* 889I or N*	20-25 m²/l
Process colour	3M™ Process Colour Series 4700	Yellow Red Blue Green	4704 4702 4703 4708	20-25 m²/l
Process colour for digital printing	Piezo Inkjet Ink Series 8800 UV	Yellow Red Blue Green Brown		
	3M™ Premium Protective Overlay Film 1160 (anti-graffiti)			Combined Thickness: 0,549 mm Rolls in various length and widths
	3M™ Dew resistant overlay film 1180			Combined Thickness: 0,549 mm Rolls in various length and widths
	3M™ Protective Overlay Film 1150			Combined Thickness: 0,549 mm Rolls in various length and widths
* Product Combinations covered in ETA 11/0426				

### 1.3 Intended use

The construction product is used to manufacture sign faces for traffic signs. The intended use includes, for example:

- retro-reflective signs, retro-reflective and trans-illuminated signs (See also EN 12899-1)
- trans-illuminated traffic bollards (See also EN 12899-2)
- road delineators with retro-reflective devices (See also EN 12899-3)
- variable message signs (See also EN 12966)

The intended use excludes road-markings as defined in EN 1436. The assumed intended working life of the product is 10 years provided that it is subjected to appropriate use and maintenance. The indications given as to the working life of the product cannot be interpreted as a guarantee given by the Manufacturer or by the Approval Body.

## 2 Characteristics of product and methods of verification

### 2.1 General

The identification tests and the assessment of fitness for use of the "3M High Intensity Prismatic Reflective Sheeting series 3930", combinations with or without "3M Electrocut Film series 1170" or "Process Colour Series 4700 or Piezo Inkjet Ink Series 8800 UV", and with or without 3M Dew Resistant Overlay Film 1180, 3M Premium Protective Overlay Film 1160 or 3M Protective Overlay Film 1150 were carried out according to the verification methods in clause 3 of this ETA.

The ETA is issued for the product on the basis of information/data deposited at UBAtc which identify the product that was assessed and judged. Changes to the production process of the product or to its components which could result in deposited information/data being incorrect, shall be notified to UBAtc before they are introduced and UBAtc will assess whether or not such changes affect the ETA and, if so, whether further assessment and/or modification to the ETA shall be necessary.

The characteristics of the product not mentioned in this ETA nor in the annexes shall correspond to the respective values laid down in the Technical Documentation of this ETA, checked by UBAtc.

Details of test results are included in the related Evaluation Report.

**2.2 Characteristics of the product "3M High Intensity Prismatic Reflective Sheeting series 3930", combinations with or without "3M Electrocut Film series 1170" or "Process Colour Series 4700 or Piezo Inkjet Ink Series 8800 UV", and with or without 3M Dew Resistant Overlay Film 1180, 3M Premium Protective Overlay Film 1160 or 3M Protective Overlay Film 1150"**

### 2.2.1 Hygiene, health and the environment

#### 2.2.1.1 Release of dangerous substances

The product complies with the provisions of Guidance Paper H ("A harmonized approach relating to Dangerous substances under the construction products directive", Edition 2002) about dangerous substances.

A written declaration of conformity in this respect was made by the manufacturer. In addition to the specific clauses relating to dangerous substances contained in this European Technical Approval, there may be other requirements applicable to the products falling within its scope (e.g. transposed European legislation and national laws, regulations and administrative provisions). In order to meet the provisions of the EU Construction Products Directive, these requirements need also to be complied with, when and where they apply.

### 2.2.2 Safety in use of "3M High Intensity Prismatic Reflective Sheeting series 3930 printed with "Process Colour series 4700"

#### 2.2.2.1 Visibility of "3M High Intensity Prismatic Reflective Sheeting series 3930 printed with "Process Colour series 4700"

##### 2.2.2.1.1 Day-time colour and Luminance Factor

The characteristics of Day-time colour and Luminance Factor (see Table 2) have been determined according to clause 3.2.1

**Table 2 - Day-time colour and Luminance Factor**

Colours		Chromaticity Coordinates				Pass/fail	Luminance Factor $\beta$
		1	2	3	4		Class
Yellow on white	x	0.494	0.470	0.513	0.545	Pass	B2
	y	0.505	0.480	0.437	0.454		$\geq 0.24$
Red on White	x	0.735	0.700	0.610	0.660	Pass	B2
	y	0.265	0.250	0.340	0.340		$\geq 0.03$
Green on White	x	0.110	0.170	0.170	0.110	Pass	B2
	y	0.415	0.415	0.500	0.500		$\geq 0.03$
Blue on White	x	0.130	0.160	0.160	0.130	Pass	B2
	y	0.090	0.090	0.140	0.140		$\geq 0.01$

#### 2.2.2.1.2 Coefficient of Retro-reflection Case A

The Coefficient of Retro-reflection - Case A (see Table 3) has been determined according to clause 3.2.2.

**Table 3 - Coefficient of retro-reflection Case A**

Colour	Class R2
Yellow on white	pass
Red on White	pass
Green on White	pass
Blue on White	pass

#### 2.2.2.1.3 Rotational symmetry

The rotational symmetry (see Table 4) has been determined according to clause 3.2.3.

**Table 4 -Rotational symmetry**

Colours	Pass/Fail
Yellow on White	Pass
Red on White	Pass
Blue on White	Pass
Green on White	Pass

**2.2.2.1.4 Impact resistance**

The Impact resistance (see Table 5) has been determined according to clause 3.2.4.

**Table 5 - Impact resistance**

Product	Colour of the sheeting	Colour of the film	Observations after the test
"3M High Intensity Prismatic Reflective Sheeting series 3930" printed with "Process Colour Series 4700"	White 3930	Yellow	Pass: no cracking has been observed outside the impact area.
		Red	
		Blue	
		Green	

**2.2.3 Durability "3M High Intensity Prismatic Reflective Sheeting serie 3930" printed with "Process Colour Series 4700"**

**2.2.3.1 Visibility after accelerated artificial weathering of "3M High Intensity Prismatic Reflective Sheeting serie 3930" printed with "Process Colour Series 4700"**

**Day-time colour and Luminance factor (see**

**2.2.3.1.1 Table 6) after accelerated artificial weathering of "3M High Intensity Prismatic Reflective Sheeting serie 3930" printed with "Process Colour Series 4700"**

The tests were performed according to clause 3.3

**Table 6 - Day-time colour and Luminance factor**

Colours		Chromaticity Coordinates				Luminance Factor $\beta$	
		1	2	3	4	Class B1	Class B2
Yellow reference	x	0.545	0.487	0.427	0.465	$\geq 0.16$	$\geq 0.24$
	y	0.454	0.423	0.483	0.534		
Yellow on White results		Pass				Class B2	
Red reference	x	0.735	0.674	0.569	0.655	$\geq 0.03$	$\geq 0.03$
	y	0.265	0.236	0.341	0.345		
Red on White results		Pass				Class B2	
Green reference	x	0.007	0.248	0.177	0.026	$\geq 0.03$	$\geq 0.03$
	y	0.703	0.393	0.362	0.399		
Green on White results		Pass				Class B2	
Blue reference	x	0.078	0.150	0.210	0.137	$\geq 0.01$	$\geq 0.01$
	y	0.171	0.220	0.160	0.038		
Blue on White results		Pass				Class B2	

**2.2.3.1.2 Coefficient of retro-reflection Case A (see Table 7) after accelerated artificial weathering of "3M High Intensity Prismatic Reflective Sheeting serie 3930" printed with "Process Colour Series 4700"**

The tests were performed according to clause 3.3. The values shall not be less than 80% of the values required for new material under clause 3.2.2, as appropriate.

**Table 7 - Coefficient of retro-reflection Case A**

Colour	Class R2
Yellow	pass
Red	pass
Green	pass
Blue	pass

**2.2.4 Safety in use of "3M High Intensity Prismatic Reflective Sheeting series 3930 printed with 3M Piezo Inkjet Ink Series 8800UV + 3M Electrocut Film 1170"**

**2.2.4.1 Visibility of "3M High Intensity Prismatic Reflective Sheeting series 3930 printed with 3M Piezo Inkjet Ink Series 8800UV + 3M Electrocut Film 1170"**

**2.2.4.1.1 Day-time colour and Luminance Factor**

The characteristics of Day-time colour and Luminance Factor (see Table 8) have been determined according to clause 3.2.1

**Table 8 - Day-time colour and Luminance factor**

Colours		Chromaticity Coordinates				Luminance Factor $\beta$	
		1	2	3	4	Class B1	Class B2
White reference	x	0.305	0.335	0.325	0.295	$\geq 0.27$	$\geq 0.40$
	y	0.315	0.345	0.355	0.325		
White results		Pass				Class B2	
Yellow reference	x	0.494	0.470	0.513	0.545	$\geq 0.16$	$\geq 0.24$
	y	0.505	0.480	0.437	0.454		
Yellow on White results		Pass				Class B2	
Red reference	x	0.735	0.700	0.610	0.660	$\geq 0.03$	$\geq 0.03$
	y	0.265	0.250	0.340	0.340		
Red on White results		Pass				Class B2	
Green reference	x	0.110	0.170	0.170	0.110	$\geq 0.03$	$\geq 0.03$
	y	0.415	0.415	0.500	0.500		
Green on White results		Pass				Class B2	
Blue reference	x	0.130	0.160	0.160	0.130	$\geq 0.01$	$\geq 0.01$
	y	0.090	0.090	0.140	0.140		
Blue on White results		Pass				Class B2	
Brown reference		0.455	0.523	0.479	0.558	0.04 – 0.06	0.03 – 0.09
		0.397	0.429	0.373	0.394		
Brown on White results		Pass				Class B1 & B2	

**2.2.4.1.2 Coefficient of Retro-reflection Case A**

The Coefficient of Retro-reflection - Case A (see Table 9) has been determined according to clause 3.2.2.

**Table 9 - Coefficient of retro-reflection Case A**

Colour	Class R2
White	pass
Yellow on white	pass
Red on White	pass
Green on White	pass
Blue on White	pass
Brown on White	pass

**2.2.4.1.3 Rotational symmetry**

The rotational symmetry (see Table 10) has been determined according to clause 3.2.3.

**Table 10 - Rotational symmetry**

Colours	Pass/Fail
White	Pass
Yellow on White	Pass
Red on White	Pass
Blue on White	Pass
Green on White	Pass
Brown on White	Pass

**2.2.4.1.4 Impact resistance**

The Impact resistance (see Table 11) has been determined according to clause 3.2.4.

**Table 11 - Impact resistance**

Product	Colour of the sheeting	Colour of the film	Observations after the test
"3M High Intensity Prismatic Reflective Sheeting series 3930 printed with 3M Piezo Inkjet Ink Series 8800UV + 3M Electrocut Film 1170"	White	3930	Pass: no cracking has been observed outside the impact area.
		Unprinted	
		Yellow	
		Red	
		Blue	
		Green	
		Brown	

**2.2.5 Durability "3M High Intensity Prismatic Reflective Sheeting series 3930 printed with 3M Piezo Inkjet Ink Series 8800UV + 3M Electrocut Film 1170"**

**2.2.5.1 Visibility after accelerated artificial weathering of "3M High Intensity Prismatic Reflective Sheeting series 3930 printed with 3M Piezo Inkjet Ink Series 8800UV + 3M Electrocut Film 1170"**

**2.2.5.1.1 Day-time colour and Luminance factor (see Table 12) after accelerated artificial weathering of "3M High Intensity Prismatic Reflective Sheeting series 3930 printed with 3M Piezo Inkjet Ink Series 8800UV + 3M Electrocut Film 1170"**

The tests were performed according to clause 3.3

**Table 12 - Day-time colour and Luminance factor**

Colours		Chromaticity Coordinates				Luminance Factor $\beta$	
		1	2	3	4	Class B1	Class B2
White reference	x	0.355	0.305	0.285	0.335	$\geq 0.27$	$\geq 0.40$
	y	0.355	0.305	0.325	0.375		
White results		Pass				Class B2	
Yellow reference	x	0.545	0.487	0.427	0.465	$\geq 0.16$	$\geq 0.24$
	y	0.454	0.423	0.483	0.534		
Yellow on White results		Pass				Class B2	
Red reference	x	0.735	0.674	0.569	0.655	$\geq 0.03$	$\geq 0.03$
	y	0.265	0.236	0.341	0.345		
Red on White results		Pass				Class B2	
Green reference	x	0.007	0.248	0.177	0.026	$\geq 0.03$	$\geq 0.03$
	y	0.703	0.393	0.362	0.399		
Green on White results		Pass				Class B2	
Blue reference	x	0.078	0.150	0.210	0.137	$\geq 0.01$	$\geq 0.01$
	y	0.171	0.220	0.160	0.038		
Blue on White results		Pass				Class B2	
Brown reference	x	0.455	0.523	0.479	0.558	0.04 – 0.06	0.03 – 0.09
	y	0.397	0.429	0.373	0.394		
Brown on White results		Pass				Class B1 & B2	

**2.2.5.1.2 Coefficient of retro-reflection Case A (see Table 13) after accelerated artificial weathering test of “3M High Intensity Prismatic Reflective Sheeting Series 3930 + 3M Piezo Inkjet Ink Series 8800UV + 3M Electrocut Film 1170”**

The tests were performed according to clause 3.3. The values shall not be less than 80% of the values required for new material under clause 3.2.2, as appropriate.

**Table 13 - Coefficient of retro-reflection Case A**

Colour	Class R2
White	pass
Yellow on white	pass
Red on White	pass
Green on White	pass
Blue on White	pass
Brown on White	pass

**2.2.6 Safety in use of “3M High Intensity Prismatic Reflective Sheeting series 3930 printed with 3M Piezo Inkjet Ink Series 8800UV + 3M Dew Resistant Overlay Film 1180”**

**2.2.6.1 Visibility of “3M High Intensity Prismatic Reflective Sheeting series 3930 printed with 3M Piezo Inkjet Ink Series 8800UV + 3M Dew Resistant Overlay Film 1180”**

**2.2.6.1.1 Day-time colour and Luminance Factor**

The characteristics of Day-time colour and Luminance Factor (see Table 14) have been determined according to clause 3.2.1



**Table 14 - Day-time colour and Luminance factor**

Colours		Chromaticity Coordinates				Luminance Factor $\beta$	
		1	2	3	4	Class B1	Class B2
White reference	x	0.305	0.335	0.325	0.295	$\geq 0.27$	$\geq 0.40$
	y	0.315	0.345	0.355	0.325		
White results		Pass				Class B1	
Yellow reference	x	0.494	0.470	0.513	0.545	$\geq 0.16$	$\geq 0.24$
	y	0.505	0.480	0.437	0.454		
Yellow on White results		Pass				Class B2	
Red reference	x	0.735	0.700	0.610	0.660	$\geq 0.03$	$\geq 0.03$
	y	0.265	0.250	0.340	0.340		
Red on White results		Pass				Class B2	
Green reference	x	0.110	0.170	0.170	0.110	$\geq 0.03$	$\geq 0.03$
	y	0.415	0.415	0.500	0.500		
Green on White results		Pass				Class B2	
Blue reference	x	0.130	0.160	0.160	0.130	$\geq 0.01$	$\geq 0.01$
	y	0.090	0.090	0.140	0.140		
Blue on White results		Pass				Class B2	
Brown reference		0.455	0.523	0.479	0.558	0.04 – 0.06	0.03 – 0.09
		0.397	0.429	0.373	0.394		
Brown on White results		Pass				Class B1 & B2	

**2.2.6.1.2 Coefficient of Retro-reflection Case A**

The Coefficient of Retro-reflection - Case A (see Table 15) has been determined according to clause 3.2.2.

**Table 15 - Coefficient of retro-reflection Case A**

Colour	Class R2
White	pass
Yellow on white	pass
Red on White	pass
Green on White	pass
Blue on White	pass
Brown on White	pass

**2.2.6.1.3 Rotational symmetry**

The rotational symmetry (see Table 16) has been determined according to clause 3.2.3.

**Table 16 - Rotational symmetry**

Colours	Pass/Fail
White	Pass
Yellow on White	Pass
Red on White	Pass
Blue on White	Pass
Green on White	Pass
Brown on White	Pass

**2.2.6.1.4 Impact resistance**

The Impact resistance (see Table 17) has been determined according to clause 3.2.4.

**Table 17 - Impact resistance**

Product	Colour of the sheeting	Colour of the film	Observations after the test
"3M High Intensity Prismatic Reflective Sheeting series 3930 printed with 3M Piezo Inkjet Ink Series 8800UV + 3M Dew Resistant Overlay Film 1180"	White 3930	Unprinted	Pass: no cracking has been observed outside the impact area.
		Yellow	
		Red	
		Blue	
		Green	
		Brown	

**2.2.7 Durability of "3M High Intensity Prismatic Reflective Sheeting series 3930 printed with 3M Piezo Inkjet Ink Series 8800UV + 3M Dew Resistant Overlay Film 1180"**

**2.2.7.1 Visibility after accelerated artificial weathering of "3M High Intensity Prismatic Reflective Sheeting series 3930 printed with 3M Piezo Inkjet Ink Series 8800UV + 3M Dew Resistant Overlay Film 1180"**

**2.2.7.1.1 Day-time colour and Luminance factor (see Table 18) after accelerated artificial weathering of "3M High Intensity Prismatic Reflective Sheeting series 3930 printed with 3M Piezo Inkjet Ink Series 8800UV + 3M Dew Resistant Overlay Film 1180"**

The tests were performed according to clause 3.3

**Table 18 - Day-time colour and Luminance factor**

Colours		Chromaticity Coordinates				Luminance Factor B	
		1	2	3	4	Class B1	Class B2
White reference	x	0.355	0.305	0.285	0.335	≥ 0.27	≥ 0.40
	y	0.355	0.305	0.325	0.375		
White results		Pass				Class B2	
Yellow reference	x	0.545	0.487	0.427	0.465	≥ 0.16	≥ 0.24
	y	0.454	0.423	0.483	0.534		
Yellow on White results		Pass				Class B2	
Red reference	x	0.735	0.674	0.569	0.655	≥ 0.03	≥ 0.03
	y	0.265	0.236	0.341	0.345		
Red on White results		Pass				Class B2	
Green reference	x	0.007	0.248	0.177	0.026	≥ 0.03	≥ 0.03
	y	0.703	0.393	0.362	0.399		
Green on White results		Pass				Class B2	
Blue reference	x	0.078	0.150	0.210	0.137	≥ 0.01	≥ 0.01
	y	0.171	0.220	0.160	0.038		
Blue on White results		Pass				Class B2	
Brown reference	x	0.455	0.523	0.479	0.558	0.04 – 0.06	0.03 – 0.09
	y	0.397	0.429	0.373	0.394		
Brown on White results		Pass				Class B2	

**2.2.7.1.2 Coefficient of retro-reflection Case A (see Table 19) after accelerated artificial weathering test of “3M High Intensity Prismatic Reflective Sheeting Series 3930 + 3M Piezo Inkjet Ink Series 8800UV + 3M Dew Resistant Overlay Film 1180”**

The tests were performed according to clause 3.3. The values shall not be less than 80% of the values required for new material under clause 3.2.2, as appropriate.

**Table 19 - Coefficient of retro-reflection Case A**

Colour	Class R2
White	pass
Yellow on white	pass
Red on White	pass
Green on White	pass
Blue on White	pass
Brown on White	pass

**2.2.8 Safety in use of “3M High Intensity Prismatic Reflective Sheeting series 3930 + 3M Premium Protective Overlay Film 1160”**

**2.2.8.1 Visibility of “3M High Intensity Prismatic Reflective Sheeting series 3930 + 3M Premium Protective Overlay Film 1160”**

**2.2.8.1.1 Day-time colour and Luminance Factor**

The characteristics of Day-time colour and Luminance Factor (see Table 20) have been determined according to clause 3.2.1

**Table 20 - Day-time colour and Luminance factor**

Colours		Chromaticity Coordinates				Luminance Factor B	
		1	2	3	4	Class B1	Class B2
White reference	x	0.305	0.335	0.325	0.295	≥ 0.27	≥ 0.40
	y	0.315	0.345	0.355	0.325		
White results	x y	Pass				Class B2	
Yellow reference	x	0.494	0.470	0.513	0.545	≥ 0.16	≥ 0.24
	y	0.505	0.480	0.437	0.454		
Yellow results	x y	Pass				Class B2	
Red reference	x	0.735	0.700	0.610	0.660	≥ 0.03	≥ 0.03
	y	0.265	0.250	0.340	0.340		
Red results	x y	Pass				Class B2	
Green reference	x	0.110	0.170	0.170	0.110	≥ 0.03	≥ 0.03
	y	0.415	0.415	0.500	0.500		
Green results	x y	Pass				Class B2	
Blue reference	x	0.130	0.160	0.160	0.130	≥ 0.01	≥ 0.01
	y	0.090	0.090	0.140	0.140		
Blue results	x y	Pass				Class B2	

**2.2.8.1.2 Coefficient of Retro-reflection Case A**

The Coefficient of Retro-reflection - Case A (see Table 21) has been determined according to clause 3.2.2.

**Table 21 - Coefficient of retro-reflection Case A**

Colour	Class R2
White	pass
Yellow	pass
Red	pass
Green	pass
Blue	pass

**2.2.8.1.3 Rotational symmetry**

The rotational symmetry (see Table 22) has been determined according to clause 3.2.3.

**Table 22 - Rotational symmetry**

Colours	Pass/Fail
White	Pass
Yellow	Pass
Red	Pass
Blue	Pass
Green	Pass

**2.2.8.1.4 Impact resistance**

The Impact resistance (see Table 23) has been determined according to clause 3.2.4.

**Table 23 - Impact resistance**

Product	Colours	Pass/fail
"3M High Intensity Prismatic Reflective Sheeting series 3930 + 3M Premium Protective Overlay Film 1160"	White	Pass: no cracking has been observed outside the impact area.
	Red	
	Yellow	
	Green	
	Blue	

**2.2.9 Durability of "3M High Intensity Prismatic Reflective Sheeting series 3930 + 3M Premium Protective Overlay Film 1160"**

**2.2.9.1 Visibility after accelerated artificial weathering of "3M High Intensity Prismatic Reflective Sheeting series 3930 + 3M Premium Protective Overlay Film 1160"**

**2.2.9.1.1 Day-time colour and Luminance factor (see Table 24) after accelerated artificial weathering of "3M High Intensity Prismatic Reflective Sheeting series 3930 + 3M Premium Protective Overlay Film 1160"**

The tests were performed according to clause 3.3.

**Table 24 - Day-time colour and Luminance factor**

Colours		Chromaticity Coordinates				Luminance Factor $\beta$	
		1	2	3	4	Class B1	Class B2
White reference	x	0.355	0.305	0.285	0.335	$\geq 0.27$	$\geq 0.40$
	y	0.355	0.305	0.325	0.375		
White results	x	Pass				Class B2	
	y						
Yellow reference	x	0.545	0.487	0.427	0.465	$\geq 0.16$	$\geq 0.24$
	y	0.454	0.423	0.483	0.534		
Yellow results	x	Pass				Class B2	
	y						
Red reference	x	0.735	0.674	0.569	0.655	$\geq 0.03$	$\geq 0.03$
	y	0.265	0.236	0.341	0.345		
Red results	x	Pass				Class B2	
	y						
Green reference	x	0.007	0.248	0.177	0.026	$\geq 0.03$	$\geq 0.03$
	y	0.703	0.393	0.362	0.399		
Green results	x	Pass				Class B2	
	y						
Blue reference	x	0.078	0.150	0.210	0.137	$\geq 0.01$	$\geq 0.01$
	y	0.171	0.220	0.160	0.038		
Blue results	x	Pass				Class B2	
	y						

**2.2.9.1.2 Coefficient of retro-reflection Case A (see Table 25) after accelerated artificial weathering test of "3M High Intensity Prismatic Reflective Sheeting Series 3930 + 3M Premium Protective Overlay Film 1160"**

The tests were performed according to clause 3.3. The values shall not be less than 80% of the values required for new material under clause 3.2.2, as appropriate.

**Table 25 - Coefficient of retro-reflection Case A**

Colour	Class R2
White	pass
Yellow	pass
Red	pass
Green	pass
Blue	pass

**2.2.10 Safety in use of "3M High Intensity Prismatic Reflective Sheeting series 3930 + 3M Electrocut Film Series 1170 + 3M Premium Protective Overlay Film 1160"**

**2.2.10.1 Visibility of "3M High Intensity Prismatic Reflective Sheeting series 3930 + 3M Electrocut Film Series 1170 + 3M Premium Protective Overlay Film 1160"**

**2.2.10.1.1 Day-time colour and Luminance Factor**

The characteristics of Day-time colour and Luminance Factor (see Table 26) have been determined according to clause 3.2.1

**Table 26 - Day-time colour and Luminance factor**

Colours		Chromaticity Coordinates				Luminance Factor $\beta$	
		1	2	3	4	Class B1	Class B2
Yellow reference	x	0.494	0.470	0.513	0.545	$\geq 0.16$	$\geq 0.24$
	y	0.505	0.480	0.437	0.454		
Yellow results	x	Pass				Class B2	
	y	Pass				Class B2	
Red reference	x	0.735	0.700	0.610	0.660	$\geq 0.03$	$\geq 0.03$
	y	0.265	0.250	0.340	0.340		
Red results	x	Pass				Class B2	
	y	Pass				Class B2	
Green reference	x	0.110	0.170	0.170	0.110	$\geq 0.03$	$\geq 0.03$
	y	0.415	0.415	0.500	0.500		
Green results	x	Pass				Class B2	
	y	Pass				Class B2	
Blue reference	x	0.130	0.160	0.160	0.130	$\geq 0.01$	$\geq 0.01$
	y	0.090	0.090	0.140	0.140		
Blue results	x	Pass				Class B2	
	y	Pass				Class B2	
Orange reference	x	0.631	0.560	0.506	0.570	$\geq 0.14$	$\geq 0.14$
	y	0.369	0.360	0.404	0.429		
Orange results	x	Pass				Class B2	
	y	Pass				Class B2	

**2.2.10.1.2 Coefficient of Retro-reflection Case A**

The Coefficient of Retro-reflection - Case A (see Table 27) has been determined according to clause 3.2.2.

**Table 27 - Coefficient of retro-reflection Case A**

Colour	Class R2
White	pass
Yellow	pass
Red	pass
Green	pass
Blue	pass
Orange	pass

**2.2.10.1.3 Rotational symmetry**

The rotational symmetry (see Table 28) has been determined according to clause 3.2.3.

**Table 28 - Rotational symmetry**

Colours	Pass/Fail
White	Pass
Yellow	Pass
Red	Pass
Blue	Pass
Green	Pass
Orange	Pass

**2.2.10.1.4 Impact resistance**

The Impact resistance (see Table 29) has been determined according to clause 3.2.4.

**Table 29 - Impact resistance**

Product	Colours	Pass/fail
"3M High Intensity Prismatic Reflective Sheeting series 3930 + 3M Electrocut Film Series 1170 + 3M Premium Protective Overlay Film 1160"	White	Pass: no cracking has been observed outside the impact area.
	Red	
	Yellow	
	Green	
	Blue	
	Orange	

**2.2.11 Durability of “3M High Intensity Prismatic Reflective Sheeting series 3930 + 3M Electrocut Film Series 1170 + 3M Premium Protective Overlay Film 1160”**

**2.2.11.1 Visibility after accelerated artificial weathering of “3M High Intensity Prismatic Reflective Sheeting series 3930 + 3M Electrocut Film Series 1170 + 3M Premium Protective Overlay Film 1160”**

**2.2.11.1.1 Day-time colour and Luminance factor (see Table 30) after accelerated artificial weathering of “3M High Intensity Prismatic Reflective Sheeting series 3930 + 3M Electrocut Film Series 1170 + 3M Premium Protective Overlay Film 1160”**

The tests were performed according to clause 3.3.

**Table 30 - Day-time colour and Luminance factor**

Colours		Chromaticity Coordinates				Luminance Factor $\beta$	
		1	2	3	4	Class B1	Class B2
White reference	x	0.355	0.305	0.285	0.335	$\geq 0.27$	$\geq 0.40$
	y	0.355	0.305	0.325	0.375		
White results	x	Pass				Class B2	
	y						
Yellow reference	x	0.545	0.487	0.427	0.465	$\geq 0.16$	$\geq 0.24$
	y	0.454	0.423	0.483	0.534		
Yellow results	x	Pass				Class B2	
	y						
Red reference	x	0.735	0.674	0.569	0.655	$\geq 0.03$	$\geq 0.03$
	y	0.265	0.236	0.341	0.345		
Red results	x	Pass				Class B2	
	y						
Green reference	x	0.007	0.248	0.177	0.026	$\geq 0.03$	$\geq 0.03$
	y	0.703	0.393	0.362	0.399		
Green results	x	Pass				Class B2	
	y						
Blue reference	x	0.078	0.150	0.210	0.137	$\geq 0.01$	$\geq 0.01$
	y	0.171	0.220	0.160	0.038		
Blue results	x	Pass				Class B2	
	y						
Orange reference	x	0.631	0.560	0.506	0.570	$\geq 0.14$	$\geq 0.14$
	y	0.369	0.360	0.404	0.429		
Orange results	x	Pass				Class B2	
	y						

**2.2.11.1.2 Coefficient of retro-reflection Case A (see Table 31) after accelerated artificial weathering test of “3M High Intensity Prismatic Reflective Sheeting Series 3930 + 3M Electrocut Film Series 1170 + 3M Premium Protective Overlay Film 1160”**

The tests were performed according to clause 3.3. The values shall not be less than 80% of the values required for new material under clause 3.2.2, as appropriate.

**Table 31 - Coefficient of retro-reflection Case A**

Colour	Class R2
White	pass
Yellow	pass
Red	pass
Green	pass
Blue	pass
Orange	pass

**2.2.12 Safety in use of “3M High Intensity Prismatic Reflective Sheeting 3930 + 3M Electrocut Film 1176 with or without 3M Protective Overlay Film”**

**2.2.12.1 Visibility of “3M High Intensity Prismatic Reflective Sheeting 3930 + 3M Electrocut Film 1176 with or without 3M Protective Overlay Film”**

**2.2.12.1.1 Day-time colour and Luminance Factor**

The characteristics of Day-time colour and Luminance Factor (see Table 32) have been determined according to clause 3.2.1

**Table 32 - Day-time colour and Luminance factor**

Colour		Chromaticity Coordinates				Luminance Factor $\beta$	
		1	2	3	4	Class B1	Class B2
Green 2 (Dark Green) reference	x	0.313	0.313	0.248	0.127	0.01 - 0.07	0.01 - 0.07
	y	0.682	0.453	0.393	0.557		
ECOF1176 results	x	Pass				Class B2	
	y						
Green 2 (Dark Green) reference	x	0.313	0.313	0.248	0.127	0.01 - 0.07	0.01 - 0.07
	y	0.682	0.453	0.393	0.557		
ECOF1176 + 1150 overlay film results	x	Pass				Class B2	
	y						
Green 2 (Dark Green) reference	x	0.313	0.313	0.248	0.127	0.01 - 0.07	0.01 - 0.07
	y	0.682	0.453	0.393	0.557		
ECOF1176 + 1160 overlay film results	x	Pass				Class B2	
	y						
Green 2 (Dark Green) reference	x	0.313	0.313	0.248	0.127	0.01 - 0.07	0.01 - 0.07
	y	0.682	0.453	0.393	0.557		
ECOF1176 + 1180 overlay film results	x	Pass				Class B2	
	y						

**2.2.12.1.2 Coefficient of Retro-reflection Case A**

The Coefficient of Retro-reflection - Case A (see Table 33) has been determined according to clause 3.2.2.

**Table 33 - Coefficient of retro-reflection Case A**

Product	Class R2 (Green2 / Dark Green)
Reflective Sheeting 3930 + ECOF1176	pass
Reflective Sheeting 3930 + ECOF1176 + 1150	pass
Reflective Sheeting 3930 + ECOF1176 + 1160	pass
Reflective Sheeting 3930 + ECOF1176 + 1180	pass

**2.2.12.1.3 Rotational symmetry**

The rotational symmetry (see Table 34) has been determined according to clause 3.2.3.

**Table 34 - Rotational symmetry**

Product	Pass/Fail
Reflective Sheeting 3930 + ECOF1176	Pass
Reflective Sheeting 3930 + ECOF1176 + 1150	Pass
Reflective Sheeting 3930 + ECOF1176 + 1160	Pass
Reflective Sheeting 3930 + ECOF1176 + 1180	Pass

**2.2.12.1.4 Impact resistance**

The Impact resistance (see Table 35) has been determined according to clause 3.2.4.

**Table 35 - Impact resistance**

Product	Observations after the test
Reflective Sheeting 3930 + ECOF1176	Pass: no cracking has been observed outside the impact area.
Reflective Sheeting 3930 + ECOF1176 + 1150	
Reflective Sheeting 3930 + ECOF1176 + 1160	
Reflective Sheeting 3930 + ECOF1176 + 1180	

**2.2.13 Durability of "3M High Intensity Prismatic Reflective Sheeting 3930 + 3M Electrocut Film 1176 with or without 3M Protective Overlay Film"**

**2.2.13.1 Visibility after accelerated artificial weathering of "3M High Intensity Prismatic Reflective Sheeting 3930 + 3M Electrocut Film 1176 with or without 3M Protective Overlay Film"**

**2.2.13.1.1 Day-time colour and Luminance factor (see Table 36) after accelerated artificial weathering of "3M High Intensity Prismatic Reflective Sheeting 3930 + 3M Electrocut Film 1176 with or without 3M Protective Overlay Film"**

The tests were performed according to clause 3.3.

**Table 36 - Day-time colour and Luminance factor**

Colour		Chromaticity Coordinates				Luminance Factor $\beta$	
		1	2	3	4	Class B1	Class B2
Green 2 reference	x	0.313	0.313	0.248	0.127	0.01 - 0.07	0.01 - 0.07
	y	0.682	0.453	0.393	0.557		
ECOF1176 results	x	Pass				Class B2	
	y						
Green 2 reference	x	0.313	0.313	0.248	0.127	0.01 - 0.07	0.01 - 0.07
	y	0.682	0.453	0.393	0.557		
ECOF1176 + 1150 overlay film results	x	Pass				Class B2	
	y						
Green 2 reference	x	0.313	0.313	0.248	0.127	0.01 - 0.07	0.01 - 0.07
	y	0.682	0.453	0.393	0.557		
ECOF1176 + 1160 overlay film results	x	Pass				Class B2	
	y						
Green 2 reference	x	0.313	0.313	0.248	0.127	0.01 - 0.07	0.01 - 0.07
	y	0.682	0.453	0.393	0.557		
ECOF1176 + 1180 overlay film results	x	Pass				Class B2	
	y						

**2.2.13.1.2 Coefficient of retro-reflection Case A (see Table 37) after accelerated artificial weathering test of "3M High Intensity Prismatic Reflective Sheeting 3930 + 3M Electrocut Film 1176 with or without 3M Protective Overlay Film"**

The tests were performed according to clause 3.3. The values shall not be less than 80% of the values required for new material under clause 3.2.2, as appropriate.

**Table 37 - Coefficient of retro-reflection Case A**

Product	Class R2 (Green2 / Dark Green)
Reflective Sheeting 3930 + ECOF1176	pass
Reflective Sheeting 3930 + ECOF1176 + 1150	pass
Reflective Sheeting 3930 + ECOF1176 + 1160	pass
Reflective Sheeting 3930 + ECOF1176 + 1180	pass

### 3 Verification Methods for determining the relevant characteristics of the construction product.

#### 3.1 Hygiene, health and the environment

##### 3.1.1 3.1.1. Release of dangerous substances

The product/kit shall comply with all relevant European and national provisions applicable for the uses for which it is brought to the market. The attention of the applicant should be drawn on the fact that for other uses or other Member States of destination there may be other requirements which would have to be respected. For dangerous substances contained in the product but not covered by an ETA, the NPD option (no performance determined) is applicable.

#### 3.2 Safety in use

##### 3.2.1 Day-time colour and Luminance Factor

The chromaticity coordinates (x, y) and the luminance factor ( $\beta$ ) are measured in accordance with CIE Publication 15.2 Colourimetry – 1986 using 45/0 geometry and shall be calculated from the total spectral radiance factors computed for CIE illuminant D65 for the CIE 1931 (2°) standard colorimetric observer.

The position of the sample in the measuring system will be indicated by an orientation mark. The orientation mark has to be adjusted 90° to the incident plane. The incident plane is formed out of the rectangle on the sample surface and the incoming light beam.

The chromaticity coordinates shall be within the colour boxes and the Luminance factor shall comply with values in Table 38.

**Table 38 - Permitted colour area in CIE 1931 diagram and Luminance factors for daylight appearance of new materials**

Colour		Chromaticity Coordinates				Luminance Factor $\beta$	
		1	2	3	4	Class B1	Class B2
White	x	0.305	0.335	0.325	0.295	$\geq 0.27$	$\geq 0.40$
	y	0.315	0.345	0.355	0.325		
Yellow	x	0.494	0.470	0.513	0.545	$\geq 0.16$	$\geq 0.24$
	y	0.505	0.480	0.437	0.454		
Red	x	0.735	0.700	0.610	0.660	$\geq 0.03$	$\geq 0.03$
	y	0.265	0.250	0.340	0.340		
Orange	x	0.631	0.560	0.506	0.570	$\geq 0.14$	$\geq 0.14$
	y	0.369	0.360	0.404	0.429		
Green	x	0.110	0.170	0.170	0.110	$\geq 0.03$	$\geq 0.03$
	y	0.415	0.415	0.500	0.500		
Green 2	x	0.313	0.313	0.248	0.127	0.01 – 0.07	0.01 – 0.07
	y	0.682	0.453	0.393	0.557		
Brown	x	0.455	0.523	0.479	0.558	0.04 – 0.06	0.03 – 0.09
	y	0.397	0.429	0.373	0.394		
Blue	x	0.130	0.160	0.160	0.130	$\geq 0.01$	$\geq 0.01$
	y	0.090	0.090	0.140	0.140		
Fluorescent Yellow	x	0.521	0.557	0.479	0.454	$\geq 0.38$	$\geq 0.38$
	y	0.424	0.442	0.520	0.491		
Fluorescent Orange	x	0.595	0.645	0.570	0.531	$\geq 0.25$	$\geq 0.20$
	y	0.351	0.355	0.429	0.414		
Fluorescent Yellow/Green	x	0.387	0.460	0.438	0.376	$\geq 0.60$	$\geq 0.70$
	y	0.610	0.540	0.508	0.568		

##### 3.2.2 Coefficient of Retroreflection

The coefficient of retro-reflection  $R'$  is measured in accordance with CIE Publication No. 54.2, Retro-reflection using CIE Standard Illuminant A. Any of the recommended apertures may be used. Measurements shall be taken at the specified observation angle  $\alpha$  and entrance angle  $\beta$ . The entrance angle  $\beta$  shall be set by its first component  $\beta_1$  with the second component  $\beta_2 = 0^\circ$ , the rotation angle  $\epsilon$  shall be  $\epsilon = 0^\circ$  and the orientation angle  $\omega_s$  shall be  $\omega_s = 0^\circ$ .

The requirements of minimum coefficient of Retro-reflection  $R'$  are specified in the following tables 39 and 40.



**Table 39 - Minimum Coefficient of Retroreflection, performance Class R2 Europe (= RA2 in EN 12899-1)**

Geometry of measurements		Colours								
$\alpha$	$\beta_1$ ( $\beta_2 = 0^\circ$ )	White	Yellow	Red	Green	Dark Green	Blue	Brown	Orange	Grey
12'	+ 5°	250	170	45	45	20	20	12	100	125
	+ 30°	150	100	25	25	15	11	8,5	60	75
	+ 40°	110	70	15	12	6	8	5,0	29	55
20'	+ 5°	180	120	25	21	14	14	8	65	90
	+ 30°	100	70	14	12	11	8	5	40	50
	+ 40°	95	60	13	11	5	7	3	20	47
2°	+ 5°	5	3	1	0,5	0,5	0,2	0,2	1,5	2,5
	+ 30°	2,5	1,5	0,4	0,3	0,3	#	#	1	1,2
	+ 40°	1,5	1,0	0,3	0,2	0,2	#	#	#	0,7

# indicates "Value greater than zero but not significant or applicable"

**Table 40 - Minimum Coefficient of Retroreflection, Performance Class RA1 Europe (EN 12899-1)**

Geometry of measurements		Colour								
$\alpha$	$\beta_1$ ( $\beta_2=0$ )	White	Yellow	Red	Green	Blue	Brown	Orange	Grey	
12'	+5°	70	50	14,5	9	4	1	25	42	
	+30°	30	22	6	3,5	1,7	0,3	10	18	
	+40°	10	7	2	1,5	0,5	#	2,2	6	
20'	+5°	50	35	10	7	2	0,6	20	30	
	+30°	24	16	4	3	1	0,2	8	14,4	
	+40°	9	6	1,8	1,2	#	#	2,2	5,4	
2°	+5°	5	3	1	0,5	#	#	1,2	3	
	+30°	2,5	1,5	0,5	0,3	#	#	0,5	1,5	
	+40°	1,5	1,0	0,5	0,2	#	#	#	0,9	

# indicates "Value greater than zero but not significant or applicable".

For material processed with process colours, with or without clear overlay film, the minimum value of the coefficient of Retro-reflection shall not be less than 70% of the values specified in the tables. For material processed with red process colour or red overlay film over yellow microprismatic sheeting, the coefficient of Retro-reflection shall not be less than 50% of the values specified in the tables.

### 3.2.3 Rotational symmetry

When measured according to clause 3.2.2, for the observation angle  $\alpha = 0.33^\circ$  and entrance angle  $\beta_1 = 5^\circ$  ( $\beta_2 = 0^\circ$ ), the ratio between the minimum and the maximum coefficient of Retro-reflection when rotating from  $\varepsilon - 75^\circ$  to  $+ 50^\circ$  in  $25^\circ$  steps, shall not be greater than 2.5.1.

### 3.2.4 Impact resistance

The test is carried out according to EN 12899-1 using a hard body having a mass of 450 g with a contact radius of 50 mm. The hard body is dropped from a height of 220 mm on a sample that shall be supported over an open area of 100 mm x 100 mm.

### 3.3 Visibility after accelerated artificial weathering

The apparatus shall be either an air cooled or water cooled Xenon arc weathering device capable of exposing samples in accordance with EN ISO 4892-2: 1994.

Preparation of test specimens should be in accordance with the general guideline given in EN ISO 4892-2: 1994.

The samples shall be exposed in accordance to EN ISO 4892-2: 1994 using the parameters given in the following table 41, for a period of 2000 hours.

**Table 41 - Artificial weathering test parameters**

Exposure parameters	Air cooled lamp	Water cooled lamp
Light/dark/water spray cycle	Continuous light with water spray on specimens for 18 minutes every 2 hours	Continuous light with water spray on specimens for 18 minutes every 2 hours
Black standard temperature during light only periods	(65 ± 3) °C using a black standard thermometer	(65 ± 3)°C using a black standard thermometer
Relative humidity	(50 ± 5) %	(50 ± 5) %
Irradiance (W/m <sup>2</sup> ) controlled at		
	over 300-400 nm range	60
over 300-800 nm range	550	630

Note 1 – Water used for specimen spray should contain no more than 1 ppm silica. Higher levels of silica may produce spotting on samples and variability in results. Water of the required purity may be obtained by distillation or by a combination of deionisation and revers osmosis.

Note 2 – Whilst irradiance levels should be set at the above levels, variations in filter ages and transmissivity, and in calibration variations, will be generally mean that irradiance error will be in the order of  $\pm 10\%$ .

After weathering, following test shall be carried out

- day time colour (according to clause 3.2.1)
- Luminance factor (according to clause 3.2.1)
- Coefficient of Retroreflection – (according to clause 3.2.2)

After exposure the coefficient of retro-reflection measured at an observation angle  $\alpha = 0.33^\circ$  (or  $\alpha = 0.2^\circ$ ) and entrance angle  $\beta_1 = 5^\circ$  and  $30^\circ$  ( $\beta_2 = 0^\circ$ ), shall not be less than 80% of the values required for new material in 3.2.2.

After exposure the chromaticity co-ordinates and Luminance factor measured according to clause 3.2.1, shall comply with the requirements specified in Table 42, as appropriate.

### 3.4 Visibility after accelerated natural (outdoor) exposure

The retro-reflective sheeting surface of the test specimens of a minimum of 20 cm x 20 cm in dimension shall be subjected to 3 years unprotected outdoor exposure, facing the equator (South) and inclined  $45^\circ$  from the vertical, taking into account the different European climatic conditions in term of temperature, UV and RH, in accordance with ISO 877:1994, using method A.

After the exposure period, the test specimens shall be washed in a 5% HCl solution for 45 seconds and then in water, using a soft brush or sponge to avoid scratching, and given a final flush with de-ionized water.

After weathering, following test shall be carried out

- day time colour (according to clause 3.2.1)
- Luminance factor (according to clause 3.2.1)
- Coefficient of Retroreflection – (according to clause 3.2.2)

After exposure the coefficient of retro-reflection measured at an observation angle  $\alpha = 0.33^\circ$  (or  $\alpha = 0.2^\circ$ ) and entrance angle  $\beta_1 = 5^\circ$  and  $30^\circ$  ( $\beta_2 = 0^\circ$ ), shall not be less than 80% of the values required for new material in 3.2.2.

After exposure the chromaticity co-ordinates and Luminance factor measured according to clause 3.2.1, shall comply with the requirements specified in Table 42, as appropriate.

**Table 42 - Permitted colour area in CIE 1931 diagram and Luminance factors for daylight appearance after accelerated weathering test or after outdoor exposure**

Colour		Chromaticity Coordinates				Luminance Factor $\beta$	
		1	2	3	4	Class B1	
						Class B2	
White	x	0.355	0.305	0.285	0.335	$\geq 0.27$	$\geq 0.40$
	y	0.355	0.305	0.325	0.375		
Yellow	x	0.545	0.487	0.427	0.465	$\geq 0.16$	$\geq 0.24$
	y	0.454	0.423	0.483	0.534		
Red	x	0.735	0.674	0.569	0.655	$\geq 0.03$	$\geq 0.03$
	y	0.265	0.236	0.341	0.345		
Orange	x	0.631	0.560	0.506	0.570	$\geq 0.14$	$\geq 0.14$
	y	0.369	0.360	0.404	0.429		
Green	x	0.007	0.248	0.177	0.026	$\geq 0.03$	$\geq 0.03$
	y	0.703	0.409	0.362	0.399		
Green 2	x	0.313	0.313	0.248	0.127	0.01 – 0.07	0.01 – 0.07
	y	0.682	0.453	0.409	0.557		
Brown	x	0.455	0.523	0.479	0.558	0.04 – 0.06	0.03 – 0.09
	y	0.397	0.429	0.373	0.394		
Blue	x	0.078	0.150	0.210	0.137	$\geq 0.01$	$\geq 0.01$
	y	0.171	0.220	0.160	0.038		
Fluorescent yellow	x	0.521	0.557	0.479	0.454	$\geq 0.38$	$\geq 0.38$
	y	0.424	0.442	0.520	0.491		
Fluorescent Orange	x	0.595	0.645	0.570	0.531	$\geq 0.25$	$\geq 0.20$
	y	0.351	0.355	0.429	0.414		
Fluorescent Yellow/Green	x	0.387	0.460	0.438	0.376	$\geq 0.50$	$\geq 0.50$
	y	0.610	0.540	0.508	0.568		

### 3.5 Temperature resistance

The photometric properties of the test specimens are determined by measuring the coefficient of Retro-reflection  $R'$  according to test method under 3.2.2. Measurements shall be taken only for the observation angle  $\alpha = 0.33^\circ$  and entrance angle  $\beta_1 = 5^\circ$  ( $\beta_2 = 0^\circ$ ;  $\epsilon = 0^\circ$ ).

The test specimens shall be then exposed in an air circulating oven for a period of 24 hours according to one of the following temperatures.

**Table 43 - Air circulating oven temperatures**

Class	Temperature
1	$80^\circ\text{C} (\pm 2)$
2	$65^\circ\text{C} (\pm 2)$
3	$50^\circ\text{C} (\pm 2)$

After exposure the test specimens shall be conditioned according ISO 139 "Standard atmospheres for conditioning and testing".

The photometric properties of the test specimens shall be re-determined by re-measuring the coefficient of Retro-reflection R' according to this clause.

When tested, the coefficient of Retro-reflection of the specimen shall be between 85% and 115% of the corresponding actual value measured before exposure.

## 4 Evaluation of conformity and CE marking

### 4.1 Attestation of conformity

The system of attestation of conformity is System 1 as described in Council Directive 89/106/EEC. Annex III, Clause 2 "Certification of Conformity of the product by an Approved Body and is detailed as followed :

#### a) Task of the manufacturer

(1) Factory Production Control (FPC), including further testing of samples taken at the factory by the manufacturer in accordance with the prescribed test plan.

#### b) Tasks of the approval body

(2) Initial Type Testing (ITT) of the product

(3) Initial inspection of the factory and of the Factory Production Control (FPC)

(4) Continuous surveillance, assessment and approval of the FPC.

### 4.2 Responsibilities

#### 4.2.1 Tasks of the manufacturer

##### 4.2.1.1 Factory Production Control (FPC)

The ETA holder has a FPC system in his plants and exercises permanent internal control of the production, including test samples in accordance with his control plan.

The control plan and the provisions taken by the ETA holder for components not produced by him have been agreed with the Approval Body and deposited with UBAtc where it is only made available to Notified Bodies involved in the conformity attestation procedure.

This control plan will be given to the Notified Body chosen by the ETA holder to perform the foreseen tasks on attestation of conformity.

The manufacturer only uses raw materials supplied with the relevant inspection documents as laid down in the control plan. The incoming raw materials are subjected to verifications by the manufacturer before acceptance.

All the elements, requirements and provisions adopted by the manufacturer are documented in a systematic manner in the form of written processes and procedures. This production control system ensures conformity with this ETA.

The results of FPC are recorded and evaluated. The records include:

- Designation of the product, raw materials and components.
- Type of control or testing
- Date of the product's manufacture and date of testing of the product or raw materials and components.

- Results of controls and testing and, if appropriate, comparison with requirements.
- Signature of person responsible for FPC.

The records shall be presented to the inspection body during the continuous surveillance. On request, they shall be presented to UBAtc.

Details of the extent, nature and frequency of testing and controls to be performed with FPC shall correspond to the control plan which is part of the technical documentation of this ETA.

#### 4.2.2 Tasks of notified bodies

##### 4.2.2.1 Initial Type Testing (ITT)

For ITT, the results of the test performed as part of the assessment for this ETA shall be used unless there are changes in the production line or plant. In such cases, the necessary new ITT has to be agreed between UBAtc and the Notified Body involved.

##### 4.2.2.2 Initial Inspection of factory and Factory Production Control (FPC)

The Notified Body shall ascertain that, in accordance with the control plan the factory (in particular, employees and equipment) and the FPC are suitable to ensure continuous and orderly manufacturing of the components according to specifications mentioned in clause 2 and 3 of this ETA.

##### 4.2.2.3 Continuous surveillance, assessment and approval of FPC.

The Notified Body should visit the factory at least once a year for surveillance. It has to be verified that the system of FPC and the specified manufacturing process are maintained, taking into account the deposited control plan. Continuous surveillance and assessment of FPC have to be performed in accordance to the control plan.

During each visit, the Notified Body shall utilize an ad-hoc check list and shall examine, among others:

- the control registers of raw materials, products in course of manufacture and finished products.
- The document attesting the respect of the control frequencies.
- The conformity of the products subjected to this ETA.

In cases where the provisions of the ETA and the control plan are no longer fulfilled, the conformity certificate should be withdrawn.

### 4.3 CE marking

The CE marking shall be affixed on the product or the packaging or on the transport documents (DDT) accompanying the components of the product. The symbol "CE" shall be followed by identification number of the Notified Body involved and shall be accompanied by the following information:

- Name or identification mark of the ETA holder.
- Legal address of the ETA holder and the manufacturing plants
- The last 2 digits of the year in which the CE marking was affixed.
- The number of the CE certificate of conformity of FPC
- The number of this ETA
- Product identification
- Product Performance referring to this ETA


	"CE"-symbol
yyyy	Number of Notified Body
<b>3M Deutschland GmbH Carl-Schurz-Str. 1 D- 41453 Neuss, Germany</b>	Name and address of the ETA-holder
<b>3M Brownwood, Texas 76801 - US</b>	Manufacturing plant
11	Two last digits of year of affixing CE Marking
0749-CPD-XXXX	Number of EC certificate of conformity
ETA N° 11/0427	ETA Number
3M™ High Intensity Prismatic Reflective Sheeting Series 3930	Product identification
Product performances: See ETA 11/0427	Use category related to weather exposure  Use category related to intended use

Figure 1 - Example of CE-Marking

## 5 Assumptions under which the fitness of the product for the intended use was favourably assessed

### 5.1 Manufacturing

3M High Intensity Prismatic Reflective Sheeting series 3930, combinations with or without 3M Electrocut Film series 1170 or Process Colour Series 4700 or Piezo Inkjet Ink Series 8800 UV, and with or without 3M Dew Resistant Overlay Film 1180 or 3M Premium Protective Overlay Film 1160 or 3M Protective Overlay Film 1150, shall correspond, as far as their composition and manufacturing process is concerned, to the products subject to the approval tests. A manufacturing process has been deposited with UBAtc.

### 5.2 Installation

#### 5.2.1 General

It is the responsibility of the ETA holder to guarantee that the information about design and installation of the systems as described in clause 2.1 of this ETA, are effectively communicated to the concerned people. This information can be given using reproductions of the respective parts of this ETA. Besides, all the data concerning the execution shall be indicated clearly on the packaging and or the enclosed instruction sheets using one or several illustrations.

In any case, it is suitable to comply with national regulations and particularly concerning national traffic code.

#### 5.2.2 Design

Most clean, smooth, relatively non-porous, flat, rigid, weather resistant surfaces are satisfactory

for proper application of High Intensity Prismatic sheeting. Those found to be most reliable and durable are properly prepared aluminum sheets and extrusions. Users are urged to carefully evaluate all other substrates for adhesion and sign durability, including impact resistance.

#### 5.2.3 Application

##### 5.2.3.1 3M High Intensity Prismatic Reflective Sheeting Reflective Sheeting Series 3930

The sheeting must be stored in a cool, dry area, preferably at 18-24°C and 30-50% RH, and should be applied within one year from delivery. Rolls should be stored horizontally in the shipping carton. Partially used rolls should be returned to the shipping carton or suspended horizontally on a rod or pipe through the core.

Unprocessed sheets should be stored flat. Finished signs and applied blanks should be stored on edge.

Package for shipment must prevent movement and chafing. Store sign packages indoors on edges. Panels or finished signs must remain dry during shipping and storage. If packaged signs become wet, unpack immediately and allow to dry.

The recognition and preparation of the substrate as well as the generalities about the application of this product series, which is fully described in the current version of the ETA holder catalogue, its technical bulletins and web site [www.3M.com/TSS](http://www.3M.com/TSS), shall be carried out in compliance with national regulations in effect, if any.

"3M High Intensity Prismatic Reflective Sheeting Reflective Sheeting Series 3930" incorporates a pressure sensitive adhesive and shall be applied to the sign substrate at room temperature (18°C) or higher by any of the following methods : mechanical squeeze roll applicator, hand squeeze roll applicator, hand application. If the heater is needed to warm to the minimum application temperature of 18°C, it must be directed at the substrate only.

Users are urged to carefully evaluate all substrates for adhesion and sign durability. "3M High Intensity Prismatic Reflective Sheeting Series 3930" is designed primarily for application to flat substrates. Sign failures caused by the substrate or improper surface preparation are not the responsibility of the ETA holder.

### 5.2.3.2 3M Electrocut film Series 1170

Electrocut film shall be stored in a cool, dry area 18-24°C and 30 – 50 % RH, and shall be used within one year from date of purchase.

These overlay films have a transparent film release liner designed to aid the cutting process and the removal of the film weed after cutting. It is recommended that inside radius corner fonts be used when cutting film. More over the ETA holder recommend the following steps :

- Adjust knife pressure to cut cleanly through the film without cutting into the liner. A 30° blade works best. Spacing between the letters or numbers should be adjusted to the aesthetic preference of the user. Consult the operating manual for instructions on how to regulate spacing. Do not cut at high speed on variable speed machines.
- Avoid sharp bends when cutting and handling film as this may cause film to release from the liner.
- After cutting is complete, lay sheets flat, face to face, back to back. Always store sheets in this manner until the sheeting has been weeded and transfer tape has been applied.
- Use a stripping tool designed for weeding films that has a blunt (not sharp) edge.
- After weeding is complete, store sheets flat, face to face, and back to back, until transfer tape has been applied.
- Transfer tape can be applied either by hand using a plastic squeegee or through a hand squeeze roll laminator. If applying the transfer tape by hand, care must be taken to always squeeze from the centre to the outside in all directions.

Series 1170 film may be applied to the sheeting either before or after the sheeting has been applied to a substrate. The use of hand squeeze roll laminator is recommended to ensure satisfactory results. Use the "split liner method" – Start in the middle of the sheet and remove half the liner to ensure proper alignment.

After Series 1170 film and sheeting have been applied, remove the transfer tape by carefully removing the tape at as low angle as possible

- When the application tape has been removed, re-roll the sign through the laminator to ensure good adhesion. Adequate pressure is a key factor relating to the ultimate strength and durability of the sheeting - to - substrate adhesion.
- A clean cutting blade is required. To remove the adhesive build up use soft cloth damped with mineral spirits, isopropyl alcohol or 3M Natural Cleaner.

### 5.2.3.3 3M Process Colour Series 880 and 3M Process Colour Series 4700

3M Process Colour Series 880I and 880N are variations of the same basic ink formulations. Both ink series use identical pigments. The difference between 880I and 880N is the solvent package, providing different drying characteristics.

Series I inks should not be blended with Series N inks. Both Series should not be blended with any other series process colours by 3M or any other manufacturer.

For screen processing, the equipment and set-up are the following: proper colour and durability is achieved by using a high grade polyester, monofilament screen fabric mesh size P.E. 157. Other size screen fabrics do not produce satisfactory colour and durability. Screen printing should be accomplished using the off-contact screening method. Direct contact screen printing should not be used. Be sure that screens, sheeting, plus screening and drying areas are dust, dirt and lint free.

For the mixing and thinning, it is important that the colours and sheeting be brought to normal ambient room temperature and humidity of the screen printing area before processing. Thin sparingly using 3M Thinner of the same series as the process colours. Do not use extenders, drying agents, or other materials as they will adversely affect performance life.

Air Drying: processed sheeting for air drying must be placed on open racks to allow adequate air circulation. High volume fans must be directed through the racks. Drying times will be increased by high humidity, low temperature, poor air circulation, heavy colour coat, and excessive thinning. Addition of drying agents is not recommended. Processed sheetings must be air dried for a minimum of 3 hours per colour.

Oven drying: Processed sheeting for oven drying must be placed on open racks individually with sufficient open space for unobstructed air flow.

All inks should not be stored at elevated temperatures and must be used within one year after the date of purchase or within the indicated shelf life.

### 5.2.3.4 3M Piezo Inkjet Ink Series 8800 UV

3M Piezo Ink Jet Ink Series 8800UV is designed as part of the 3M MCS™ (Matched Component System) for application using the Durst Rho 161TS / 162TS Printer onto 3M High Intensity Prismatic Reflective Sheeting Series 3930 BEFORE mounting the sheeting onto a sign substrate. These UV-curable inks are durable, weather-resistant, and have excellent color retention when used in combination with 3M ElectroCut™ Film 1170 or 3M Dew Resistant Overlay Film 1180 as an overlaminates.

Detailed printing guidelines in order to achieve traffic sign colors according to this ETA can be obtained in the latest Product Bulletin for 3M Piezo Ink Jet Ink Series 8800UV.

Above mentioned overlaminates must always be applied, following below instructions:

To avoid a silvering artifact (trapped air between ink layer and overlaminates), the lamination process should be conducted under a controlled set of conditions.

Recommended laminator specifications and set-up:

- Roll diameter: max. 350 mm; Roll weight: approximately 80 kg; Roll width: 1400-1600 mm
- Core size: 3 inches; 2 Take-up shafts; 2 Supply shafts
- Heatable top roller: min. 45°C; Pressure: > 8 bar

3M Piezo Ink Jet Ink Series 8800UV should not be stored at elevated temperatures. It must be used within the indicated shelf life.

**5.2.3.5 Protective Overlay Films: 3M Dew Resistant Overlay Film 1180 and 3M Premium Protective Overlay Film 1160 and 3M Protective Overlay Film 1150**

Protective Overlay film shall be stored in a cool, dry area at 18-24°C and 30 – 50 % RH, and shall be used within one year from date of purchase.

The application of any Protective Overlay Film is typically done on the finished signface (after the application of the ECF and ink) but PRIOR to the application of frames or sign assembly. The Protective Overlay Film must be applied using a squeeze roll applicator (see 3M Information Folder IF1.13). The split liner method may be used.

3M Dew Resistant Overlay Film Series 1180 provides a very sensitive active layer that is prone to contamination and scratches. This active layer is therefore protected by a water-soluble, clear protective coating. This protective coating should remain on the sign as long as possible. Ideally it should be removed after the traffic sign is erected. If the protective coating is removed before sign erection, precautions have to be taken to prevent any contamination or mechanical damage. Due to the protective coating, it is strongly recommended NOT to overlap the Dew Resistant Overlay Film.

## Annex I Use options

VISIBILITY		USE OPTIONS												
		Option 1	Option 2	Option 3	Option 4	Option 5	Option 6	Option 7	Option 8	Option 9	Option 10	Option 11	Option 12	
Daytime Colour		Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	
Luminance factor		Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	Tm 4.4.2.1 Lv 5.4.1	
Fluorescence Luminance factor		NOT TO BE TESTED	NOT TO BE TESTED	Tm 4.4.2.2 Lv 5.4.2	NOT TO BE TESTED	Tm 4.4.2.2 Lv 5.4.2	NOT TO BE TESTED	NOT TO BE TESTED	Tm 4.4.2.2 Lv 5.4.2	NOT TO BE TESTED	NOT TO BE TESTED	NOT TO BE TESTED	NOT TO BE TESTED	
Night-time colour		NOT TO BE TESTED	Tm 4.4.2.3 Lv 5.4.3	Tm 4.4.2.3 Lv 5.4.3	Tm 4.4.2.3 Lv 5.4.3	Tm 4.4.2.3 Lv 5.4.3	Tm 4.4.2.3 Lv 5.4.3	NOT TO BE TESTED	NOT TO BE TESTED	NOT TO BE TESTED	NOT TO BE TESTED	Tm 4.4.2.3 Lv 5.4.3	NOT TO BE TESTED	
Coefficient of Retro-reflection-Case A or Case B		Tm 4.4.2.4 Lv 5.4.4	Tm 4.4.2.4 Lv 5.4.4	Tm 4.4.2.4 Lv 5.4.4	Tm 4.4.2.4 Lv 5.4.4	Tm 4.4.2.4 Lv 5.4.4	Tm 4.4.2.4 Lv 5.4.4	Tm 4.4.2.4 Lv 5.4.4	Tm 4.4.2.4 Lv 5.4.4	Tm 4.4.2.4 Lv 5.4.4	Tm 4.4.2.4 Lv 5.4.4	Tm 4.4.2.4 Lv 5.4.4	Tm 4.4.2.4 Lv 5.4.4	
Colour Contrast Factors		NOT TO BE TESTED	Tm 4.4.2.5 Lv 5.4.5	NOT TO BE TESTED	Tm 4.4.2.5 Lv 5.4.5	NOT TO BE TESTED	Tm 4.4.2.5 Lv 5.4.5	Tm 4.4.2.5 Lv 5.4.5	NOT TO BE TESTED	Tm 4.4.2.5 Lv 5.4.5	NOT TO BE TESTED	NOT TO BE TESTED	NOT TO BE TESTED	
Total luminous transmittance		NOT TO BE TESTED	NOT TO BE TESTED	NOT TO BE TESTED	Tm 4.4.2.6 Lv 5.4.6	NOT TO BE TESTED	Tm 4.4.2.6 Lv 5.4.6	NOT TO BE TESTED	NOT TO BE TESTED	Tm 4.4.2.6 Lv 5.4.6	NOT TO BE TESTED	NOT TO BE TESTED	NOT TO BE TESTED	
Impact resistance		Tm 4.4.2.7 Lv 5.4.7	Tm 4.4.2.7 Lv 5.4.7	Tm 4.4.2.7 Lv 5.4.7	Tm 4.4.2.7 Lv 5.4.7	Tm 4.4.2.7 Lv 5.4.7	Tm 4.4.2.7 Lv 5.4.7	Tm 4.4.2.7 Lv 5.4.7	Tm 4.4.2.7 Lv 5.4.7	Tm 4.4.2.7 Lv 5.4.7	Tm 4.4.2.7 Lv 5.4.7	Tm 4.4.2.7 Lv 5.4.7	NOT TO BE TESTED	
<b>DURABILITY</b>														
Temperature resistance		NOT TO BE TESTED	Tm 4.7.1 Lv 5.7.1	Tm 4.7.1 Lv 5.7.1	Tm 4.7.1 Lv 5.7.1	NOT TO BE TESTED	NOT TO BE TESTED	Tm 4.7.1 Lv 5.7.1	Tm 4.7.1 Lv 5.7.1	Tm 4.7.1 Lv 5.7.1	Tm 4.7.1 Lv 5.7.1	Tm 4.7.1 Lv 5.7.1	NOT TO BE TESTED	
Visibility after accelerated weathering test	Day-time colour (*)	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	
	Luminance factor (*)	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	Tm 4.7.2 + 4.4.2.1 Lv 5.7.2	
	Fluorescence Luminance factor (*)	NOT TO BE TESTED	NOT TO BE TESTED	Tm 4.7.2 + 4.4.2.2 Lv 5.7.3	NOT TO BE TESTED	Tm 4.7.2 + 4.4.2.2 Lv 5.7.3	NOT TO BE TESTED	NOT TO BE TESTED	NOT TO BE TESTED	4.7.2 + 4.4.2.2 Lv 5.7.3	NOT TO BE TESTED	NOT TO BE TESTED	NOT TO BE TESTED	NOT TO BE TESTED
	Coefficient of Retro-reflection (*)	Tm 4.7.2 + 4.4.2.4 Lv 5.7.4	Tm 4.7.2 + 4.4.2.4 Lv 5.7.4	Tm 4.7.2 + 4.4.2.4 Lv 5.7.4	Tm 4.7.2 + 4.4.2.4 Lv 5.7.4	Tm 4.7.2 + 4.4.2.4 Lv 5.7.4	Tm 4.7.2 + 4.4.2.4 Lv 5.7.4	Tm 4.7.2 + 4.4.2.4 Lv 5.7.4	Tm 4.7.2 + 4.4.2.4 Lv 5.7.4	Tm 4.7.2 + 4.4.2.4 Lv 5.7.4	Tm 4.7.2 + 4.4.2.4 Lv 5.7.4	Tm 4.7.2 + 4.4.2.4 Lv 5.7.4	Tm 4.7.2 + 4.4.2.4 Lv 5.7.4	Tm 4.7.2 + 4.4.2.4 Lv 5.7.4
Visibility after outdoor exposure	Day-time colour	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	
	Luminance factor	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	
	Coefficient of Retro-reflection	Tm 4.7.3 + 4.4.2.1 Lv 5.7.2	Tm 4.7.3 + 4.4.2.4 Lv 5.7.4	Tm 4.7.3 + 4.4.2.4 Lv 5.7.4	Tm 4.7.3 + 4.4.2.4 Lv 5.7.4	Tm 4.7.3 + 4.4.2.4 Lv 5.7.4	Tm 4.7.3 + 4.4.2.4 Lv 5.7.4	Tm 4.7.3 + 4.4.2.4 Lv 5.7.4	Tm 4.7.3 + 4.4.2.4 Lv 5.7.4	Tm 4.7.3 + 4.4.2.4 Lv 5.7.4	Tm 4.7.3 + 4.4.2.4 Lv 5.7.4	Tm 4.7.3 + 4.4.2.4 Lv 5.7.4	Tm 4.7.3 + 4.4.2.4 Lv 5.7.4	
	Fluorescence Luminance factor	NOT TO BE TESTED	NOT TO BE TESTED	Tm 4.7.3 + 4.4.2.2 Lv 5.7.3	NOT TO BE TESTED	Tm 4.7.3 + 4.4.2.2 Lv 5.7.3	NOT TO BE TESTED	NOT TO BE TESTED	NOT TO BE TESTED	Tm 4.7.3 + 4.4.2.2 Lv 5.7.3	NOT TO BE TESTED	NOT TO BE TESTED	NOT TO BE TESTED	NOT TO BE TESTED

Tm = Test method

Lv = Limit values

(\*) = The tests after accelerated exposure can be carried out for the first issue of the ETA in order not to delay the issuing process. In case of further issue of the ETA, then these tests shall be carried out after the outdoor exposure.

**Table 1 – Use options**

Note: The assessment of the product is performed according to the content of the Option chosen by the manufacturer. Details concerning the characteristics foreseen by the chosen Option as well as test results will be included in an Annex of the ETA.